

2MS0N Shrink Film



PRODUCT BULLETIN

Description

Hostaphan® 2MS0N is an untreated polyester film. It combines high strength, durability, and excellent chemical resistance with a balanced high shrinkage.


Performance

Hostaphan® 2MS0N has excellent slip and handles well even in the thinnest gauges. It is designed for use in applications that require a high, balanced MD/TD shrinkage.

Benefits

- Balanced high shrinkage
- Excellent handling characteristics
- Available gauges: 65, 150

Schematic of Hostaphan® 2MS0N



PET Base Film
(Moderate Haze)

Typical Properties of Hostaphan® 2MS0N Film

The Hostaphan® 2MS0N property values below are typical measurements. Further guidance on functional behavior by end use, film processing, standard roll configuration and gauges is available through a Mitsubishi Polyester Film Sales Representative.

Property		Unit of Measure	Typical Value	Test Method
Area Yield		in ² •mil/lb m ² •µm/kg	19,800 717	ASTM D 4321
Tensile Strength	MD	psi kg/cm ²	33,000 2,300	ASTM D 882
Yield Strength (F5)	MD	psi kg/cm ²	14,000 1,000	ASTM D 882
Ultimate Elongation	MD TD	%	90 60	ASTM D 882
Modulus	MD	psi kg/cm ²	500,000 35,000	ASTM D 882
Coefficient of Friction A/B	Static Kinetic	--	0.40 0.36	ASTM D 1894
Shrinkage	MD	%	6.0	5 min. at 75°C
	TD	%	6.0	
	MD	%	33.0	5 min. at 105°C
	TD	%	33.0	
	MD	%	35.0	5 min. at 150°C
TD	%	35.0		
	MD	%	37.0	5 min. at 175°C
	TD	%	37.0	
	MD	%	38.0	5 min. at 190°C
	TD	%	38.0	
Density		g/cm ³	1.395	ASTM D 1505
Total Haze*		%	65 ga. 150 ga.	ASTM D-1003
			4.0 6.5	

* Values for reference data only. Contact a Mitsubishi Polyester Film Sales Representative for actual gauges available.

Approved ZL 8/09



PO Box 1400 • Hood Road • Greer SC 29652 • 864-879-5000 • 864-879-5006 • www.m-petfilm.com

Hostaphan is a registered trademark of Hoechst AG and is licensed to Mitsubishi Polyester Film, Inc. The information contained herein is believed to be true and accurate, but all data, recommendations and suggestions are provided without guarantee, since the conditions of use are beyond our control and can affect the performance and properties of our products. The user is solely responsible for confirming that our product is suitable for the intended end use, and for compliance with all legal regulations and patents. Other than compliance with published Mitsubishi Polyester Film, Inc. specifications for one year following purchase, and except as required by law, MITSUBISHI POLYESTER FILM, INC. MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, OR ANY WARRANTY ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If a product is found to be defective during the warranty period, user's sole remedy and our sole obligation is, at our option, replacement of the affected product or refund of the purchase price. Except as required by law, we are not liable for any damage, harm or loss resulting from our product, whether direct, indirect, consequential, incidental or special, and irrespective of legal theory asserted, including strict liability, contract, warranty, or negligence.

©2000, 2008 Mitsubishi Polyester Film, Inc. All rights reserved.