



Description

Hostaphan® 4607 and 4667 are ultra clear polyester films that are chemically primed to provide enhanced adhesion for both aqueous and solvent based inks, coatings and adhesives. They combine high durability, optical clarity and balanced shrinkage for improved flatness after thermal processing.


Performance

Hostaphan® 4607 and 4667 are designed to meet the needs of a changing market as more industries move to aqueous coating and printing systems. These are glass-clear products with one or two side chemical primer to provide the slip necessary to handle and wind an unfilled film. The chemical primer promotes adhesion to water based and solvent based coatings and inks. These products can be metallized, printed and coated for use in a wide variety of enduses, such as labels and reprographics.

Benefits

- Available in one side primed (4607) and two side primed (4667)
- Adhesion promotion for aqueous and solvent systems
- Excellent flatness
- Excellent color and clarity
- Environmentally friendly

Schematic of Hostaphan® 4607



Typical Properties of Hostaphan® 4607 and 4667 Films

The Hostaphan® 4607 and 4667 property values below are typical measurements. Further guidance on series selection, functional behavior by end use, film processing, standard roll configuration and gauges is available through a Mitsubishi Polyester Film Sales Representative.

Property		Unit of Measure	Typical Value	Test Method
Area Yield		in ² •mil/lb m ² •µm/kg	19,800 717	ASTM D 4321
Tensile Strength	MD	psi kg/cm ²	30,000 2,110	ASTM D 882
Yield Strength (F5)	MD	psi kg/cm ²	15,000 1,050	ASTM D 882
Ultimate Elongation	MD	%	150	ASTM D 882
Modulus	MD	psi kg/cm ²	500,000 35,200	ASTM D 882
Coefficient of Friction (A/B)	Kinetic	--	0.45	ASTM D 1894
Shrinkage	MD TD	%	1.0 1.0	30 min. at 150°C
Density		g/cm ³	1.395	ASTM D 1505
Total Haze*		%	200 gauge 0.40 300 " 0.48 400 " 0.58 500 " 0.66 700 " 0.85	ASTM D-1003

* Values for reference data only. Contact a Mitsubishi Polyester Film Sales Representative for actual gauges available.



PO Box 1400 • Hood Road • Greer SC 29652 • 864-879-5000 • 864-879-5006 • www.m-petfilm.com

Hostaphan is a registered trademark of Hoechst AG and is licensed to Mitsubishi Polyester Film, Inc. The information contained herein is believed to be true and accurate, but all data, recommendations and suggestions are provided without guarantee, since the conditions of use are beyond our control and can affect the performance and properties of our products. The user is solely responsible for confirming that our product is suitable for the intended end use, and for compliance with all legal regulations and patents. Other than compliance with published Mitsubishi Polyester Film, Inc. specifications for one year following purchase, and except as required by law, MITSUBISHI POLYESTER FILM, INC. MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, OR ANY WARRANTY ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If a product is found to be defective during the warranty period, user's sole remedy and our sole obligation is, at our option, replacement of the affected product or refund of the purchase price. Except as required by law, we are not liable for any damage, harm or loss resulting from our product, whether direct, indirect, consequential, incidental or special, and irrespective of legal theory asserted, including strict liability, contract, warranty, or negligence.

©2000, 2008 Mitsubishi Polyester Film, Inc. All rights reserved.