

# 2261N General Purpose Film

Mitsubishi Chemical America, Inc.

# **Product Bulletin**

### **Description**

Hostaphan® 2261N is an untreated polyester film. It combines high strength and durability, good dimensional stability, and excellent chemical resistance.


#### **Performance**

Hostaphan® 2261N has excellent slip and good dimensional stability over a wide temperature range and handles well even in the thinnest gauges.

#### **Benefits**

- Good dimensional stability
- Excellent handling characteristics

## Schematic of Hostaphan® 2261N



### Typical Properties of Hostaphan® 2261N Film

The Hostaphan® 2261N property values below are typical measurements. Further guidance on series selection, functional behavior by end use, film processing, standard roll configuration and gauges is available through a Polyester Film Sales Representative.

Property		Unit of Measure		Typical Value	Test Method
Area Yield		in²∙mil/lb m²∙µm/kg		19,800 717	ASTM D 4321
Tensile Strength	MD	psi kg/cm²		32,000 2,250	ASTM D 882
Yield Strength (F5)	MD	psi kg/cm²		15,000 1,050	ASTM D 882
Ultimate Elongation	MD	%		110	ASTM D 882
Modulus	MD	psi kg/cm²		600,000 42,200	ASTM D 882
Coefficient of Friction A/B	Static Kinetic			0.40 0.36	ASTM D 1894
Shrinkage	MD TD	%		1.9 0.4	30 min. at 150°C
Density		g/cm³		1.395	ASTM D 1505
Total Haze*		%	48 gauge 60 " 72 " 92 " 118 " 142 "	3.0 3.2 3.3 3.6 4.2 5.0	ASTM D-1003

<sup>\*</sup> Values for reference data only. Contact a Polyester Film Sales Representative for actual gauges available. Approved DJ 3/2014

Mitsubishi Chemical America, Inc. • PO Box 1400 • 2001 Hood Road • Greer, SC 29652 • 864-879-5000 • 864-879-5006 • www.m-petfilm.com

Hostaphan is a registered trademark of Hoechst AG and is licensed to Mitsubishi Chemical America, Inc. The information contained herein is believed to be true and accurate, but all data, recommendations and suggestions are provided without guarantee, since the conditions of use are beyond our control and can affect the performance and properties of our products. The user is solely responsible for confirming that our product is suitable for the intended end use, and for compliance with published Mitsubishi Chemical America, Inc. specifications for one year following purchase, if properly handled, and except as required by law, MITSUBISHI CHEMICAL AMERICA, INC. MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, OR ANY WARRANTY ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If a product is found to be non-conforming during the warranty period, user's sole remedy and our sole obligation is, at our option, replacement of the affected product or refund of the purchase price. Except as required by law, we are not liable for any damage, harm or loss resulting from our product, whether direct, indirect, consequential, incidental or special, and irrespective of legal theory asserted, including strict liability, contract, warranty, or negligence.