

Mitsubishi Chemical America, Inc.


Description

Hostaphan® 2PA2N polyester film is chemically primed on both sides for adhesion to polyolefins. This clear film combines high strength and flexibility with good dimensional stability and excellent chemical resistance.

Performance

Hostaphan® 2PA2N film is designed for thermal lamination or extrusion coating with polyolefins. The chemically primed surfaces adhere strongly to polymers and blends commonly used in packaging sealant layers. In particular, the primed surfaces demonstrate outstanding adhesion to polypropylene and linear low density polyethylene (LLDPE). This film is used in hot nip lamination and extrusion coating for packaging applications.

Schematic of Hostaphan® 2PA2N



Benefits

- Outstanding adhesive bond after thermal lamination to LLDPE or polypropylene
- Bond strength is not degraded by exposure to heat and moisture. Eliminates moisture sensitivity issues of PEI-based primers
- Moderate adhesion to LDPE and mild adhesion to HDPE. Polyethylene blends can tune bond strength for peelable constructions
- No corona, atmospheric treatment, or additional priming required prior to extrusion coating or lamination.
- Lower extrusion coating temperatures since it is not necessary to oxidize the polyethylene melt for adhesion
- Replace solvent-based or polyurethane adhesive systems with thermal lamination in retort structures
- Available thickness range: 0.47-7 mil (12-175 micron)

FDA Status

Both sides of Hostaphan® 2PA2N can be used for direct food contact applications subject to limitations found in 21 CFR 177.1630 and in accordance with good manufacturing practices. For more information, contact a Polyester Film Sales Representative.

Typical Properties of Hostaphan® 2PA2N Film

The Hostaphan® 2PA2N property values below are typical measurements. Further guidance on series selection, functional behavior by end use, film processing, standard roll configuration and gauges is available through a Polyester Film Sales Representative.

Property		Unit of Measure	Typical Value	Test Method
Area Yield	0.47 mil (12 µm)	ft ² /lb m ² /kg	286.5 58.7	ASTM D 4321
	2.0 mil (50 µm)	ft ² /lb m ² /kg	68.8 14.1	
Tensile Strength	MD	psi kg/cm ²	28,000 1,980	ASTM D 882
Yield Strength (F5)	MD	psi kg/cm ²	15,000 1,050	ASTM D 882
Ultimate Elongation	MD	%	120	ASTM D 882
Modulus	MD	psi kg/cm ²	500,000 35,200	ASTM D 882
Coefficient of Friction A/B	Static	--	0.35	ASTM D 1894
	Kinetic	--	0.32	
Shrinkage	MD	%	1.6	30 min. at 150°C
	TD		0.4	
Density		g/cm ³	1.395	ASTM D 1505
Total Haze*	0.47 mil (12 µm)	%	2.7	ASTM D-1003
	2.0 mil (50 µm)		7.0	
Primed Surface Energy		dynes/cm	30	Water Contact Angle (EoS Model)
Peel Strength from Polypropylene		lbf/inch g/inch	> 6.5 >3000	ASTM D-903 (180° Peel)
Peel Strength from LLDPE		lbf/inch g/inch	> 6.5 >3000	ASTM D-903 (180° Peel)
Peel Strength from LDPE		lbf/inch g/inch	0.85 390	ASTM D-903 (180° Peel)
Peel Strength from HDPE		lbf/inch g/inch	0.25 120	ASTM D-903 (180° Peel)

* Values for reference data only. Contact a Polyester Film Sales Representative for actual gauges available.

Approved MG 1/2021

Mitsubishi Chemical America, Inc. • PO Box 1400 • 2001 Hood Road • Greer, SC 29652 • 864-879-5000 • 864-879-5006 • www.m-petfilm.com

Hostaphan is a registered trademark of Hoechst AG and is licensed to Mitsubishi Chemical America, Inc. The information contained herein is believed to be true and accurate, but all data, recommendations and suggestions are provided without guarantee, since the conditions of use are beyond our control and can affect the performance and properties of our products. The user is solely responsible for confirming that our product is suitable for the intended end use, and for compliance with all legal regulations and patents. Other than compliance with published Mitsubishi Chemical America, Inc. specifications for one year following purchase, if properly handled, and except as required by law, MITSUBISHI CHEMICAL AMERICA, INC. MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, OR ANY WARRANTY ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If a product is found to be non-conforming during the warranty period, user's sole remedy and our sole obligation is, at our option, replacement of the affected product or refund of the purchase price. Except as required by law, we are not liable for any damage, harm or loss resulting from our product, whether direct, indirect, consequential, incidental or special, and irrespective of legal theory asserted, including strict liability, contract, warranty, or negligence.

©2021, 2022 Mitsubishi Chemical America, Inc. All rights reserved.