

3ACK Release Liner Film



PRODUCT BULLETIN

Description

Hostaphan® 3ACK polyester film is release coated on one side. Along with high strength, flexibility, and chemical resistance, this product provides excellent slip and good dimensional stability over a wide temperature range. FDA end uses are not permitted, since this product has not been tested for food and drug use applications.


Performance

The release coating on Hostaphan® 3ACK has been uniquely designed to release aqueous ceramic cast coatings commonly used in the electronics industry.

Benefits

- Excellent handling characteristics
- Clear distortion free coating
- Ultra thin, highly cured coating which does not smear

Schematic of Hostaphan® 3ACK



Product Safety Information

WARNING:

Release coated film is very slippery. Do not discard scrap film on the floor. Injury may result if stepped on.

Typical Properties of Hostaphan® 3ACK Film

The Hostaphan® 3ACK property values below are typical measurements. Further guidance on series selection, functional behavior by end use, film processing, standard roll configuration and gauges is available through a Mitsubishi Polyester Film Sales Representative.

Property		Unit of Measure	Typical Value	Test Method	
Area Yield		in ² •mil/lb m ² •mm/kg	19,800 717	ASTM D 4321	
Tensile Strength	MD	psi kg/cm ²	30,000 2,100	ASTM D 882	
Yield Strength (F5)	MD	psi kg/cm ²	15,000 1,050	ASTM D 882	
Ultimate Elongation	MD	%	115	ASTM D 882	
Modulus	MD	psi kg/cm ²	550,000 38,700	ASTM D 882	
Coefficient of Friction	Kinetic	--	0.4	ASTM D 1894	
Shrinkage	MD TD	%	1.5 0.4	30 min. at 150°C	
Density		g/cm ³	1.395	ASTM D 1505	
Total Haze		%	118 gauge	2.8	ASTM D-1003
Release From Coated Side		g/in	< 500	T-peel from proprietary acrylic adhesive	
Smear		--	None	Haze observed when rubbed once with index finger	
Rub-off		--	None	Coating removed when rubbed hard with index finger	

* Values for reference data only. Contact a Mitsubishi Polyester Film Sales Representative for actual gauges available

Approved – RC 6/2018



PO Box 1400 • Hood Road • Greer SC 29652 • 864-879-5000 • 864-879-5006 • www.m-petfilm.com

Hostaphan is a registered trademark of Hoechst AG and is licensed to Mitsubishi Polyester Film, Inc. The information contained herein is, to the best of our knowledge, true and accurate, but all recommendations or suggestions are made without guarantee, since the conditions of use are beyond our control. There is no implied warranty of merchantability or fitness for purpose of the product or products described herein. In submitting this information, no liability is assumed or license or other rights express or implied given with respect to any existing or pending patent, patent applications or trademarks. The observance of all legal regulations and patents is the responsibility of the user.

©2000- 2016, 2018 Mitsubishi Polyester Film, inc. All rights reserved.