

Mitsubishi Chemical America, Inc.

Product Bulletin


Description

Hostaphan® 7333UV ultra-clear polyester film is chemically modified on one side for handleability and improved adhesion to acrylic hard coatings. This film is highly effective at blocking the transmission of UV radiation. It combines high strength and durability, good dimensional stability, and excellent chemical resistance with very low haze.

Performance


Hostaphan® 7333UV is designed for applications where UV protection with high clarity is required. This film is utilized in metallized products, solar control laminates and other applications that benefit from low haze, surface smoothness and brilliance.

Schematic of Hostaphan® 7333UV



Benefits

- Excellent clarity and color
- Modified surface for improved slip
- Enhanced adhesion to scratch-resistant coatings
- Reduced potential for scratching during web handling
- Retention of UV blocking capability for a least one year in outdoor applications*
- Multiyear durability in outdoor applications*



^{*}based on accelerated aging studies using QUV340 irradiation, average UV flux 78 W/m² (300-400nm integrated intensity), continuous exposure at 60°C.

Typical Properties of Hostaphan® 7333UV Film

The Hostaphan® 7333UV property values below are typical measurements. Further guidance on series selection, functional behavior by end use, film processing, standard roll configuration and gauges is available through a Polyester Film Sales Representative.

Property		Unit of Measure	7	Typical Value	Test Method
Area Yield		ft²/lb m²/kg	92 gauge (23 μm)	149.5 30.6	ASTM D 4321
Tensile Strength	MD	psi kg/cm²		33,000 2,320	ASTM D 882
Yield Strength (F5)	MD	psi kg/cm²		15,500 1,090	ASTM D 882
Ultimate Elongation	MD	%		115	ASTM D 882
Modulus	MD	psi kg/cm²		550,000 38,700	ASTM D 882
Coefficient of Friction (A/B)	Static Kinetic			0.45 0.40	ASTM D 1894
Shrinkage	MD TD	%		1.6 0.4	30 min. at 150°C
Shrinkage	MD TD	%		4.2 1.7	30 min. at 190°C
Density		g/cm³		1.395	ASTM D 1505
Transmission		%		89	ASTM D-1003
Total Haze*		%	48 gauge (12.5 μm) 92 gauge (23 μm) 142 guage (36 μm)	0.9 1.2 1.5	ASTM D-1003
UV Cut Off @320 nm*		%	48 gauge (12.5 μm) 92 gauge (23 μm) 142 gauge (36 μm)	5.0 0.3 < 0.03	ASTM D-2008-12
UV Cut Off @365 nm*		%	48 gauge (12.5 μm) 92 gauge (23 μm) 142 gauge (36 μm)	14 3 0.4	ASTM D-2008-12

^{*} Values for reference data only. Contact a Polyester Film Sales Representative for actual gauges available. Approved MG 8/2021

Mitsubishi Chemical America, Inc. • PO Box 1400 • 2001 Hood Road • Greer, SC 29652 • 864-879-5000 • 864-879-5006 • www.m-petfilm.com

Hostaphan is a registered trademark of Hoechst AG and is licensed to Mitsubishi Chemical America, Inc. The information contained herein is believed to be true and accurate, but all data, recommendations and suggestions are provided without guarantee, since the conditions of use are beyond our control and can affect the performance and properties of our products. The user is solely responsible for confirming that our product is suitable for the intended end use, and for compliance with all legal regulations and patents. Other than compliance with published Mitsubishi Chemical America, Inc. specifications for one year following purchase, if property handled, and except as required by law, MITSUBISHI CHEMICAL AMERICA, INC. MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, OR ANY WARRANTY ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If a product is found to be non-conforming during the warranty period, user's sole remedy and our sole obligation is, at our option, replacement of the affected product or refund of the purchase price. Except as required by law, we are not liable for any damage, harm or loss resulting from our product, whether direct, indirect, consequential, incidental or special, and irrespective of legal theory asserted, including strict liability, contract, warranty, or negligence.