

Mitsubishi Chemical America, Inc.

Description

Hostaphan® ML01 is a matte polyester film with a reduced gloss surface.

Performance

Hostaphan® ML01 film is designed for markets requiring a light matte surface.


FDA Status

Hostaphan® ML01 can be used for direct food contact applications subject to limitations found in 21 CFR 177.1630. For more information, contact a Polyester Film Sales Representative.

Benefits

- Medium gloss surface
- Good dimensional stability
- Excellent handling characteristics
- Low TD shrinkage
- Standard gauges: 92, 200

Schematic of Hostaphan® ML01



PET Base Film
(Translucent)

Typical Properties of Hostaphan® ML01 Film

The Hostaphan® ML01 property values below are typical measurements. Further guidance on series selection, functional behavior by end use, film processing, standard roll configuration and gauges is available through a Polyester Film Sales Representative.

Property		Unit of Measure	Typical Value	Test Method
Nominal Thickness*		gauge	92 200	ASTM E 252
Total Transmission		%	92 gauge 200 89 87	ASTM D 1003
60° Gloss		%	92 gauge 200 95 85	Gloss Meter
Tensile Strength	MD TD	psi psi	26,000 34,000	ASTM D 882
Modulus	MD TD	psi psi	440,000 560,000	ASTM D 882
Ultimate Elongation	MD TD	%	120 100	ASTM D 882
Shrinkage		MD TD	% 1.9 0.4	30 min. at 150°C
Coefficient of Friction (A/B)	Kinetic	--	0.25	ASTM D 1894

* Values for reference data only. Contact a Polyester Film Sales Representative for actual gauges available.

Approved KT 3/2014

Mitsubishi Chemical America, Inc. • PO Box 1400 • 2001 Hood Road • Greer, SC 29652 • 864-879-5000 • 864-879-5006 • www.m-petfilm.com

Hostaphan is a registered trademark of Hoechst AG and is licensed to Mitsubishi Chemical America, Inc. The information contained herein is believed to be true and accurate, but all data, recommendations and suggestions are provided without guarantee, since the conditions of use are beyond our control and can affect the performance and properties of our products. The user is solely responsible for confirming that our product is suitable for the intended end use, and for compliance with all legal regulations and patents. Other than compliance with published Mitsubishi Chemical America, Inc. specifications for one year following purchase, if properly handled, and except as required by law, MITSUBISHI CHEMICAL AMERICA, INC. MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, OR ANY WARRANTY ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If a product is found to be non-conforming during the warranty period, user's sole remedy and our sole obligation is, at our option, replacement of the affected product or refund of the purchase price. Except as required by law, we are not liable for any damage, harm or loss resulting from our product, whether direct, indirect, consequential, incidental or special, and irrespective of legal theory asserted, including strict liability, contract, warranty, or negligence.

©2000 – 2008, 2014, 2021, 2022 Mitsubishi Chemical America, Inc. All rights reserved.