

Description

Hostaphan® MT01 is a matte polyester film with a medium gloss surface.

Performance


Hostaphan® MT01 film is designed for markets requiring a matte surface.

FDA Status

Hostaphan® MT01 can be used for direct food contact applications subject to limitations found in 21 CFR 177.1630. Contact a Polyester Film Sales Representative for more information.

Benefits

- Medium gloss surface
- Good dimensional stability
- Excellent handling characteristics
- Low TD shrinkage
- Standard gauges: 48, 142, 200, 300

Schematic of Hostaphan® MT01

PET Base Film
(Translucent)

Typical Properties of Hostaphan® MT01 Film

The Hostaphan® MT01 property values below are typical measurements. Further guidance on series selection, functional behavior by end use, film processing, standard roll configuration and gauges is available through a Polyester Film Sales Representative.

Property		Unit of Measure	Typical Value	Test Method
Nominal Thickness*		gauge	48 142 200 300	ASTM E 252
Total Transmission		%	48 gauge 87 142 " 85 200 " 84 300 " 65	ASTM D 1003
60° Gloss		%	48 gauge 38 142 " 32 200 " 27 300 " 25	Gloss Meter
Area Yield		in ² / lb	48 gauge 41254 142 " 13945 200 " 9901 300 " 6601	ASTM D 4321
Tensile Strength	MD TD	psi psi	26,000 34,000	ASTM D 882
Modulus	MD TD	psi psi	440,000 560,000	ASTM D 882
Ultimate Elongation	MD TD	%	120 100	ASTM D 882
Shrinkage		MD TD	% 1.9 0.4	30 min. at 150°C
Coefficient of Friction (A/B)	Static Kinetic	-- --	0.30 0.25	ASTM D 1894
Density		g/cm ³	1.40	ASTM D 1505

* Please contact a Polyester Film Sales Representative for all available gauges.

Approved KE 5/2016

Mitsubishi Chemical America, Inc. • PO Box 1400 • 2001 Hood Road • Greer, SC 29652 • 864-879-5000 • 864-879-5006 • www.m-petfilm.com

Hostaphan is a registered trademark of Hoechst AG and is licensed to Mitsubishi Chemical America, Inc. The information contained herein is believed to be true and accurate, but all data, recommendations and suggestions are provided without guarantee, since the conditions of use are beyond our control and can affect the performance and properties of our products. The user is solely responsible for confirming that our product is suitable for the intended end use, and for compliance with all legal regulations and patents. Other than compliance with published Mitsubishi Chemical America, Inc. specifications for one year following purchase, if properly handled, and except as required by law, MITSUBISHI CHEMICAL AMERICA, INC. MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, OR ANY WARRANTY ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If a product is found to be non-conforming during the warranty period, user's sole remedy and our sole obligation is, at our option, replacement of the affected product or refund of the purchase price. Except as required by law, we are not liable for any damage, harm or loss resulting from our product, whether direct, indirect, consequential, incidental or special, and irrespective of legal theory asserted, including strict liability, contract, warranty, or negligence.

©2000-2008, 2012, 2021 Mitsubishi Chemical America, Inc. All rights reserved.