



Description

Hostaphan® MT0R is a matte polyester film with a medium gloss surface. It is chemically primed on one side for enhanced adhesion.

Performance

Hostaphan® MT0R film is designed for markets requiring a matte surface. The primed surface provides enhanced adhesion to solvent based inks, coatings, and adhesives, as well as vacuum deposited metal. Printing fine detail images on MT0R can only be printed with flexographic printing, rotogravure printing of detailed images is not recommended on this film.


FDA Status

Both sides of Hostaphan® MT0R can be used for direct food contact applications subject to limitations found in 21 CFR 177.1630. Contact your Mitsubishi Polyester Film Sales Representative for more information.

Benefits

- Medium gloss surface
- Good dimensional stability
- Excellent handling characteristics
- Low TD shrinkage
- Inks, barrier coatings, adhesives and metallization may be applied to the chemically primed side without additional priming or corona treatment.
- Standard gauge: 48

Schematic of Hostaphan® MT0R



Typical Properties of Hostaphan® MT0R Film

The Hostaphan® MT0R property values below are typical measurements. Further guidance on series selection, functional behavior by end use, film processing, standard roll configuration and gauges is available through a Mitsubishi Polyester Film Sales Representative.

Property		Unit of Measure	Typical Value	Test Method
Nominal Thickness*		gauge	48	ASTM E 252
Total Transmission		%	87	ASTM D 1003
60° Gloss		%	38	Gloss Meter
Area Yield		in ² /lb	41254	ASTM D 4321
Tensile Strength	MD TD	psi psi	26,000 34,000	ASTM D 882
Modulus	MD TD	psi psi	440,000 560,000	ASTM D 882
Ultimate Elongation	MD TD	%	120 65	ASTM D 882
Shrinkage	MD TD	%	1.9 0.4	30 min. at 150°C
Coefficient of Friction (A/B)	Static Kinetic	-- --	0.30 0.25	ASTM D 1894
Density		g/cm ³	1.40	ASTM D 1505
Surface Energy		coated side	43	Internal test (contact angle)

* Values for reference data only. Contact a Mitsubishi Polyester Film Sales Representative for actual gauges available.

Approved KE 5/16



PO Box 1400 • Hood Road • Greer SC 29652 • 864-879-5000 • 864-879-5006 • www.m-petfilm.com

Hostaphan is a registered trademark of Hoechst AG and is licensed to Mitsubishi Polyester Film, Inc. The information contained herein is believed to be true and accurate, but all data, recommendations and suggestions are provided without guarantee, since the conditions of use are beyond our control and can affect the performance and properties of our products. The user is solely responsible for confirming that our product is suitable for the intended end use, and for compliance with all legal regulations and patents. Other than compliance with published Mitsubishi Polyester Film, Inc. specifications for one year following purchase, and except as required by law, MITSUBISHI POLYESTER FILM, INC. MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, OR ANY WARRANTY ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If a product is found to be defective during the warranty period, user's sole remedy and our sole obligation is, at our option, replacement of the affected product or refund of the purchase price. Except as required by law, we are not liable for any damage, harm or loss resulting from our product, whether direct, indirect, consequential, incidental or special, and irrespective of legal theory asserted, including strict liability, contract, warranty, or negligence.

©2000, 2008 Mitsubishi Polyester Film, Inc. All rights reserved.