

Mitsubishi Chemical America, Inc.

Product Bulletin

Description

Hostaphan® MT66K7 polyester film is a dual surface film that has a rough, matte surface on one side with an antistatic coating, and a smooth surface on the other side with a silicone release coating. It combines differential surface roughness with high strength and durability, good dimensional stability, and excellent chemical resistance.

Performance

Hostaphan® MT66K7 polyester film is designed for use in industrial PSA and other lamination applications.

Benefits

- Two side differential surface roughness
- Matte surface for roughness and low gloss
- Matte surface with antistatic coating
- Smooth surface for high gloss
- Smooth surface with silicone release coating

Schematic of Hostaphan® MT66K7



Typical Properties of Hostaphan® MT66K7 Film

The Hostaphan® MT66K7 property values below are typical measurements. Further guidance on series selection, functional behavior by end use, film processing, standard roll configuration and gauges is available through a Polyester Film Sales Representative.

Property	Unit of Measure		Typical Value	Test Method
Area Yield	200 gauge (2 mil, 50 um)	in ² /lb m ² /kg	9,901 14.1	ASTM D 4321
Tensile Strength	MD	psi kg/cm ²	30,000 2,100	ASTM D 882
Yield Strength (F5)	MD	psi kg/cm ²	15,000 1,050	ASTM D 882
Ultimate Elongation	MD	%	115	ASTM D 882
Modulus	MD	psi kg/cm ²	550,000 38,700	ASTM D 882
Shrinkage	MD TD	%	2.5 0.5	30 min. at 190°C
Density		g/cm ³	1.395	ASTM D 1505
Total Haze	200 gauge	%	35.0	ASTM D-1003
R _a Matte*	200 gauge	nm	400 - 500	
R _a Smooth*	200 gauge	nm	40 - 50	
Silicone Release smooth side		gf/inch	25 15	Specialty Adhesive @ 400 in/min T-peel from Tesa 7475 @ 20 in./min.
Conductivity rough side		uamps@500V	0.7	

* Values for reference data only. Contact a Polyester Film Sales Representative for additional information.

Approved DJ 4/2024

Mitsubishi Chemical America, Inc. • PO Box 1400 • 2001 Hood Road • Greer, SC 29652 • 864-879-5000 • 864-879-5006 • www.m-petfilm.com

Hostaphan is a registered trademark of Hoechst AG and is licensed to Mitsubishi Chemical America, Inc. The information contained herein is believed to be true and accurate, but all data, recommendations and suggestions are provided without guarantee, since the conditions of use are beyond our control and can affect the performance and properties of our products. The user is solely responsible for confirming that our product is suitable for the intended end use, and for compliance with all legal regulations and patents. Other than compliance with published Mitsubishi Chemical America, Inc. specifications for one year following purchase, if properly handled, and except as required by law, MITSUBISHI CHEMICAL AMERICA, INC. MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, OR ANY WARRANTY ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If a product is found to be non-conforming during the warranty period, user's sole remedy and our sole obligation is, at our option, replacement of the affected product or refund of the purchase price. Except as required by law, we are not liable for any damage, harm or loss resulting from our product, whether direct, indirect, consequential, incidental or special, and irrespective of legal theory asserted, including strict liability, contract, warranty, or negligence.