


W54B White Opaque Film



PRODUCT BULLETIN

Description

Hostaphan® W54B is a white opaque polyester film, two side chemically primed for enhanced adhesion to solvent based inks and coatings. It is characterized by high mechanical strength and good dimensional stability.

Performance

Hostaphan® W54B film is designed for markets requiring whiteness and opacity. The chemical primer provides enhanced adhesion to solvent based systems. It is used in many applications including labels, pre-paid cards, and imaging as a basis for ink jet film, and as a high quality replacement for paper as a backing in blister packs.


Benefits

- Whiteness and opacity
- High mechanical strength and good dimensional stability
- Enhanced adhesion for solvent based inks and coatings
- Excellent flatness

Restrictions - USA

Hostaphan® W Series films are not recommended for use with light sensitive coatings such as those containing silver halides, diazos or photopolymers without appropriate testing.

Schematic of Hostaphan® W54B



Typical Properties of Hostaphan® W54B Film

The Hostaphan® W54B property values below are typical measurements. Further guidance on series selection, functional behavior by end use, film processing, standard roll configuration and gauges is available through a Mitsubishi Polyester Film Sales Representative. The following values are not binding specifications and may vary.

Property		Unit of Measure	Typical Value	Test Method
Tensile Strength	MD	psi N/mm ²	21,000 150	ASTM D 882
	TD	psi N/mm ²	31,000 240	
Yield Strength (F5)	MD	psi N/mm ²	13,000 90	ASTM D 882
	TD	psi N/mm ²	15,200 105	
Ultimate Elongation	MD	%	160	ASTM D 882
	TD		90	
Shrinkage	MD	%	1.0	DIN 40634 30 min. at 150°C
	TD		1.0	
Density		g/cm ³	1.42	ASTM D 1505
Transmission		%	200 ga. 700 ga.	ASTM D 1003
			20.0 4.0	
Luminance (L*)		-	200 ga. 700 ga.	DIN 5033
			95 96	
Yellowness Index		-	200 ga. 700 ga.	ASTM D 1925
			-9.0 -8.0	
Gloss		-	52	DIN 67530 Angle of measure 60°
Opacity		-	200 ga. 700 ga.	90 99
			90 99	

Approved RC - 5/2016



PO Box 1400 • Hood Road • Greer SC 29652 • 864-879-5000 • 864-879-5006 • www.m-petfilm.com

Hostaphan is a registered trademark of Hoechst AG and is licensed to Mitsubishi Polyester Film, Inc. The information contained herein is believed to be true and accurate, but all data, recommendations and suggestions are provided without guarantee, since the conditions of use are beyond our control and can affect the performance and properties of our products. The user is solely responsible for confirming that our product is suitable for the intended end use, and for compliance with all legal regulations and patents. Other than compliance with published Mitsubishi Polyester Film, Inc. specifications for one year following purchase, and except as required by law, MITSUBISHI POLYESTER FILM, INC. MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, OR ANY WARRANTY ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If a product is found to be defective during the warranty period, user's sole remedy and our sole obligation is, at our option, replacement of the affected product or refund of the purchase price. Except as required by law, we are not liable for any damage, harm or loss resulting from our product, whether direct, indirect, consequential, incidental or special, and irrespective of legal theory asserted, including strict liability, contract, warranty, or negligence.

©2000 – 2013, 2016 Mitsubishi Polyester Film, Inc. All rights reserved.